



# C-Dur Antislip

Antislip, wear resistant and white ceiling side

## PRODUCT DETAILS

Available in	P4, P5, P6(U7) <sup>1</sup> & P8 <sup>2</sup>
Thickness	38 mm
Base Plate	5280 x 2070 mm 5600 x 2070 mm
Available stock product	2400 x 600 mm 2550 x 1000 mm

## CHARACTERISTICS<sup>3</sup>

Connection	tongue/groove 2/4 sides feather/groove 2/4 sides
Bending strength	15 N/mm <sup>2</sup>
Modulus of elasticity	2600 N/mm <sup>2</sup>
Internal bond	0,35 N/mm <sup>2</sup>
Formaldehyde emission	E1
Fire protection top/bottom	Cfl-s1 / D-s2,d0
Slip resistance	R12
Wear resistance	AC4

<sup>1</sup> - P6 Board of Unilin with improved characteristics.

<sup>2</sup> - Unofficial Berghoef name for board with density  $\pm 750\text{kg/m}^3$ .

<sup>3</sup> - All values mentioned are based on the U7<sup>1</sup> Unilin Board.

## GENERAL INFORMATION

### CHIPBOARD CLASSIFICATION ACCORDING TO EN 312

P4	Constructive boards for use in dry areas ( $\pm 640\text{kg/m}^3$ ).
P5	Constructive board for use in dry or humid areas.
P6	Heavy duty board for use in dry areas ( $\pm 700\text{kg/m}^3$ ).
P7	Heavy duty board for use in dry or humid areas.
(P8) <sup>2</sup>	Extra heavy duty board for use in dry areas ( $\pm 750\text{kg/m}^3$ ).

### SLIP RESISTANCE ACCORDING TO DIN 51130

Class	Friction Coefficient ( $\mu$ )	Platform angle
R9	0,00 - 0,18	3° - 10°
R10	0,18 - 0,34	10° - 19°
R11	0,34 - 0,51	19° - 27°
R12	0,51 - 0,71	27° - 35°

### FIRE CLASSIFICATION ACCORDING TO EN 13501

Euro Std.	Smoke	Contribution to fire	Fire protection
Bfl	s1 or s2	Very limited	Excellent
Cfl	s1 or s2	Limited	Improved
Dfl	s1 or s2	Average	Standard

- s1: almost no smoke production • s2: average smoke production • s3: large smoke production
- d0: no droplets • d1: droplets burn less than 10 seconds
- d2: droplets burn longer than 10 seconds

### WEAR RESISTANCE ACCORDING TO EN 13329

Class	IP	Use
AC 2	IP $\geq$ 1500	Domestic
AC 3	IP $\geq$ 2000	Commercial (moderate - heavy)
AC 4	IP $\geq$ 4000	Industrial (heavy - very heavy)

**berghoef**  
INTERNATIONAL

### BERGHOEF HOUT BV

Bolstoen 11,  
1046 AS Amsterdam  
THE NETHERLANDS  
Tel.: +31 (0)20 506 17 77

### BERGHOEF GmbH

Hardrain 3,  
76476 Bischweier  
GERMANY  
Tel.: +49 (0)7222 406560

[info@berghoef.com](mailto:info@berghoef.com)

[www.berghoef.com](http://www.berghoef.com)