

DECLARATION OF PERFORMANCE	
Reference :	DOPMezzanineU7StandardTGv1
Commercial name :	Mezzanine U7 Standard TG
Product type :	Melamine faced tongue and groove panel
Reference standard :	Wood Based Panel - EN 13986 Annex A Table A.4
CE Class :	P6
Field of application :	Internal use as a structural component in dry conditions
AVCP Class :	2+
Certification number:	1161-CPR-1326
Produced at:	Breestraat 4,B-8710 Wielsbeke Ingelmunstersteenweg 299,B-8780 Oostrozebeke

Essential Characteristic	Unit	Reference	Thickness range (mm)		
			25	>25-32	>32
Bending strength	N/mm ²	EN 312-table 9	16	16	15
Bending stiffness	N/mm ²	EN 312-table 9	2700	2700	2600
Internal bond	N/mm ²	EN 312-table 9	0,40	0,40	0,35
Swelling in thickness, 24h	%	EN 312-table 9	15	15	14
Formaldehyde emission class	Class	EN 13986-table B1	E1	E1	E1
Formaldehyde content	mg/100g	EN 120	≤ 8	≤ 8	≤ 8
Reaction to fire	Class	EN 13501-1	D-s2,d0	D-s2,d0	D-s2,d0
Reaction to fire (Flooring)	Class	EN 13501-1	C _{fl} -s1	C _{fl} -s1	C _{fl} -s1
Water vapour permeability μ	wet	EN 13986 - table 9	15	15	15
	dry		50	50	50
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	NPD
Sound absorption α		EN 13986 - table 10	0,10/0,25	0,10/0,25	0,10/0,25
Thermal conductivity λ	W/m.K	EN 13986 - table 11	0,13	0,13	0,13
Strength - tension ft	N/mm ²	EN 12369-1	8,3	8,3	7,8
Strength - compression fc	N/mm ²	EN 12369-1	12,2	12,2	11,9
Strength - bending f _m	N/mm ²	EN 12369-1	12,5	12,5	11,7
Strength - panel shear f _v	N/mm ²	EN 12369-1	6,5	6,5	6
Strength - planar shear f _r	N/mm ²	EN 12369-1	1,7	1,7	1,7
Stiffness - tension E _t	N/mm ²	EN 12369-1	1900	1900	1800
Stiffness - compression E _c	N/mm ²	EN 12369-1	1900	1900	1800
Stiffness - bending E _m	N/mm ²	EN 12369-1	3300	3300	3100
Stiffness - panel shear G _v	N/mm ²	EN 12369-1	950	950	900
Impact resistance	Class	EN 12871	NPD	NPD	NPD
Punishing shear strength R _{mean}	N/mm ²	EN 1195	NPD	NPD	NPD
Punishing shear strength F _{ser,k}	N/mm ²	EN 1195	NPD	NPD	NPD
Punishing shear strength F _{max,k}	N/mm ²	EN 1195	NPD	NPD	NPD
Linear expansion δ _{130,85}	mm/m	EN 318	< 4	< 4	< 4
Mechanical durability (kmod; kdef)		Shall be taken from :	EN 1995-1-1	EN 1995-1-1	EN 1995-1-1
Biological durability	Service Class	EN 335	1	1	1
Content of PCP	ppm	EN 13986-5.18	<5	<5	<5

Informative Characteristic	Unit	Reference	Thickness range (mm)		
			>25-32	>25-32	>32
Formaldehyde content	mg/100g	EN 120	< 8 mg/100g DS		

Version date :
19/01/2019

Lode De Boe,
President UNILIN bvba, division panels

