



C-Dur White

Untreated top side and white ceiling side

PRODUCT DETAILS

Quality	P4
Thickness	38 mm
Base Plate	
Article nr: 150215	5280 x 2070 mm
Article nr: 150202	5600 x 2070 mm

CHARACTERISTICS

Connection	tongue/groove 2/4 sides feather/groove 2/4 sides
Bending strength	9 N/mm ²
Modulus of elasticity	1500 N/mm ²
Internal bond	0,20 N/mm ²
Formaldehyde emission	E1
Fire protection top/bottom	Dfl-s1 / D-s2,d0
Slip resistance	n.a.
Wear resistance	n.a.

Also available with FSC or PFEC certificate on request.



GENERAL INFORMATION

SLIP RESISTANCE ACCORDING TO DIN 51130

Class	Friction Coefficient (μ)	Platform angle
R9	0,00 - 0,18	3° - 10°
R10	0,18 - 0,34	10° - 19°
R11	0,34 - 0,51	19° - 27°
R12	0,51 - 0,71	27° - 35°

CHIPBOARD CLASSIFICATION ACCORDING TO EN 312

P4	Constructive boards for use in dry areas ($\pm 640\text{kg/m}^3$).
P5	Constructive board for use in dry or humid areas.
P6	Heavy duty board for use in dry areas ($\pm 700\text{kg/m}^3$).
P7	Heavy duty board for use in dry or humid areas .

FIRE CLASSIFICATION ACCORDING TO EN 13501

Euro Std.	Smoke	Contribution to fire	Fire protection
Bfl	s1 or s2	Very limited	Excellent
Cfl	s1 or s2	Limited	Improved
Dfl	s1 or s2	Average	Standard

▪ s1: almost no smoke production ▪ s2: average smoke production ▪ s3: large smoke production
 ▪ d0: no droplets ▪ d1: droplets burn less than 10 seconds
 ▪ d2: droplets burn longer than 10 seconds

WEAR RESISTANCE EN 13329

Class	IP	Quality
AC 2	IP \geq 1500	Domestic
AC 3	IP \geq 2000	Commercial (moderate - heavy)
AC 4	IP \geq 4000	Industrial (heavy - very heavy)

berghoef
INTERNATIONAL

BERGHOEF HOUT BV
Bolstoen 11,
1046 AS Amsterdam
THE NETHERLANDS
Tel.: +31 (0)20 506 17 77

BERGHOEF GmbH
Hardrain 3,
76476 Bischweier
GERMANY
Tel.: +49 (0)7222 406560

info@berghoef.com

www.berghoef.com